


colour chart ArtCreation Essentials oil colour

Zinc white 104 +++ ☑ PW4	Titanium white 105 +++ ■ PW6, PW4	Lemon yellow 205 ++ ☑ PY3/PW6	Yellow 200 ++ ☑ PY74/PW6	Deep yellow 202 ++ ☑ PY74/PO43/PW6	Naples yellow red 224 +++ ☑ PBr24	Orange 235 ++ ☑ PO34/PY3	Vermilion 311 ++ ☑ PO34/PR57:1	Scarlet 334 ++ ☑ PO34/PR57:1
Deep rose 362 +++ ☑ PV19/PV23	Carmine 318 ++ ☑ PR83	Violet 536 ++ ☑ PV23/PV19	Ultramarine 504 +++ ☐ PB29	Cobalt blue (ultram.) 512 +++ ☑ PB29	Phthalo blue 570 +++ ☐ PB15	Prussian blue 508 ++ ☐ PB27	Sèvres blue 530 +++ ☑ PB15/PW6	Phth. turquoise blue 565 +++ ☑ PB15/PG7/PW6
Bluish green deep 637 +++ ☑ PB15/PG7	Yellowish green 617 ++ ☑ PG7/PY74	Light green 601 ++ ☑ PG7/PY3	Permanent green 662 ++ ☑ PG7/PY3	Emerald green 615 +++ ■ PG36/PY154/PW6	Viridian 616 +++ ☐ PG7	Olive green 620 +++ ☐ PG7/PY43/PY128	Yellow ochre 227 +++ ■ PY42	Raw sienna 234 +++ ☐ PY42/PR101
Raw umber 408 +++ ☐ PY42/PR101/PBk11	Burnt sienna 411 +++ ☐ PR101	Burnt umber 409 +++ ☐ PR101/PBk11	Light oxide red 339 +++ ■ PR101	Cold grey 717 +++ ■ PBk9/PW6	Warm grey 718 +++ ■ PBk9/PR101/PY128/PW6	Payne's grey 708 +++ ☑ PBk11/PB29/PV19	Ivory black 701 +++ ■ PBk9	Lamp black 702 +++ ■ PBk9/PB29

Explanations of the signs
from left to right

Example:



Degree of lightfastness

- +++ = 100 years completely lightfast under museum conditions
- ++ = 25 - 100 years lightfast under museum conditions
- + = 10 - 25 years lightfast under museum conditions
- ° = 0 - 10 years lightfast under museum conditions

The lightfastness of all these colours has been tested in accordance with ASTM Standards D4303.

Transparency/opacity

- 1 = transparent
- 2 = semi-transparent
- 3 = semi-opaque
- 4 = opaque

205 = colour number

PY3 = pigments used